



Architectural Coatings

SPEED-WALL Interior Latex Paint Flat

GENERAL DESCRIPTION

SPEED-WALL Latex Paint Flat is an economical interior vinyl acrylic paint designed to for the high volume multi-family housing market. This professional quality flat finish delivers high production with its good dry hide and quick dry and recoat when applied by brush, roller or spray. This low-VOC, low odor paint enables a space to be painted while occupied. Ideal for use on properly prepared interior walls and ceilings. Use on primed or previously painted properly prepared drywall, plaster, masonry, wood, and metal surfaces.

RECOMMENDED SUBSTRATES

Table with 2 columns: Substrate and Recommendation. Includes Aluminum, Concrete, Galvanized Metal, Gypsum Wallboard Drywall, Masonry, Plaster, Steel, and Wood.

CONFORMANCE STANDARDS

VOC compliant in all regulated areas
Can help earn LEED® 2009 credits

APPLICATION INFORMATION

Mix thoroughly before use. May be applied by brush, roller or airless spray. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Material Safety Data Sheet (MSDS) information prior to use.

Application Equipment: Apply with a high quality brush, roller or by airless spray equipment.

Airless Spray: For spray application use tip 0.015" - 0.017" Adjust pressure as needed. Spray equipment must be handled with due care and in accordance with manufacturer's recommendation.

Brush: Polyester/Nylon Brush
Roller: 3/8" - 1/2" nap roller cover
Thinning: Thinning is not required

Permissible temperatures during application:
Material: 50 to 90°F 10 to 32°C
Ambient: 50 to 90°F 10 to 32°C
Substrate: 50 to 90°F 10 to 32°C

TINTING AND BASE INFORMATION

Table with 2 columns: GPS Code and Color. Includes GPS-2000 (White), GPS-2110 (Base 1), GPS-2300 (Base 2), GPS-2020 (Antique White), GPS-2010 (Swiss Coffee).

Tint the appropriate base with universal colorants.

PRODUCT DATA

Table with 2 columns: Property and Value. Includes Product Type (Vinyl Acrylic Resin), Finish (Flat), Sheen (Gloss: 2.5 units maximum @ 85°), Volume Solids* (16% +/- 1%), Weight Solids* (31% +/- 1%), VOC* (<50 g/L), and Weight/Gallon* (10 lbs. (1.22 kg/L)).

*Product data calculated on GPS-2000

THEORETICAL COVERAGE @ 1 mil dry: 257 sq. ft./gal. (6 sq. m/L)

PRACTICAL COVERAGE: Apply at 300-400 sq. ft./gal. (7-10 sq. m/L). Actual coverage may vary depending on surface texture, porosity, and application method. For best hiding, tint primers towards finish coat.

Table with 2 columns: Property and Value. Includes Wet Film Thickness (4.0 - 5.3 mils), Wet Microns (102 - 135), Dry Film Thickness (0.6 - 0.8 mils), and Dry Microns (15 - 20).

Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing.

Table with 2 columns: Property and Value. Includes Drying Time (Dry time @ 77°F (25°C); 50% relative humidity), To Touch (30 minutes), and To Recoat (2 hours).

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement.

CLEANUP: Clean hands and tools immediately with warm, soapy water. Clean spills right away with a damp cloth.

WASHING INSTRUCTIONS: After 30 days or when paint has fully cured, areas may be washed using a non-abrasive, mild detergent solution and cellulose sponge.

DISPOSAL: Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

FLASH POINT: Over 200°F (93°C)

FEATURES / BENEFITS

Features

- Less than 50 g/L VOC
Low odor
Flat finish
Quick dry and recoat time
Uniform flat finish
Applies easily
Can help earn LEED 2009 credits

Benefits

- Meets the most stringent VOC regulations nationwide
Ideal for painting in occupied spaces
Hides minor surface imperfections
Turns units faster resulting in less down time
Provides a quality finished appearance
User friendly applicator
Contributes to sustainable design

GENERAL SURFACE PREPARATION

Surfaces to be coated must be dry, clean, sound, and free from all contamination including loose and peeling paint, dirt, grease, oil, wax, concrete curing agents and bond breakers, chalk, efflorescence, mildew, rust, product fines, and dust. Remove loose paint, chalk, and efflorescence by wire brushing, scraping, sanding, and/or pressure washing. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Feather back all rough edges to sound surface by sanding.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. In Canada contact a regional Health Canada office. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

NEW SURFACES:

Drywall: Joint compound must dry for two days before priming. Prime with the appropriate latex drywall primer.

Wood: Set nails, fill with latex spackle. Sand smooth. Dust clean. Prime with appropriate latex or alkyd wood primer.

Concrete, Plaster and Masonry: Cure at least 30 days before painting. pH must be 10.0 or lower. Roughen slick poured or precast concrete and remove sealers by chemical cleaning or abrasive method such as sandsweeping. Rinse thoroughly with water and allow to dry. Must be internally dry. Remove loose aggregate. Prime with the appropriate latex bonding primer for concrete. Fill concrete block with a latex block filler. Prime plaster with the appropriate latex primer for plaster.

Steel: Performance over hand or power tool cleaned surfaces is dependent on the degree of cleaning. Prime with the appropriate solvent-borne metal primer.

Galvanized Metal and Aluminum: Clean off oils and other contaminants. Prime with the appropriate waterborne or solventborne primer.

PREVIOUSLY PAINTED SURFACES: Wash to remove contaminants. Rinse thoroughly with water and allow to dry. Dull glossy areas by light sanding. Remove sanding dust. Remove loose paint. Prime bare areas with primer specified under **NEW SURFACES**.

LIMITATIONS OF USE

Apply when air and surface temperatures are between 50°F (10°C) and 90°F (32°C). Do not apply when the surface or air temperature is below 50°F (10°C).

PROTECT FROM FREEZING.

PACKAGING

1-Gallon (3.78 L)
5-Gallon (18.9 L)

PRECAUTIONS

WARNING! CAUSES EYE, SKIN AND RESPIRATORY TRACT IRRITATION. MAY BE HARMFUL IF SWALLOWED. USE ONLY WITH ADEQUATE VENTILATION. KEEP OUT OF THE REACH OF CHILDREN. For emergency information call (800) 545-2643. Note: These warnings encompass the product series. Prior to use, read and follow product-specific MSDS and label information. If sanding, wear a dust mask to avoid breathing of sanding dust. Do not breathe vapors or spray mist. Ensure fresh air entry during application and drying. Avoid contact with eyes and skin. If you experience eye watering, headaches, or dizziness, leave the area. If properly used, a respirator may offer additional protection. Obtain professional advice before using. Close container after each use. **FIRST AID:** For skin contact, wash thoroughly with soap and water. If any product remains, gently rub with petroleum jelly, vegetable or mineral/baby oil then wash again with soap and water. Repeat as needed. Remove contaminated clothing. For eye contact, flush immediately with plenty of water for at least 15 minutes. Get medical attention. If swallowed, get medical attention immediately. If inhalation causes discomfort, remove to fresh air. If discomfort persists or breathing difficulty occurs, get medical attention. KEEP FROM FREEZING. DS26-0306

Glidden Professional, the Glidden Professional Logo and SPEED-WALL are registered trademarks of the PPG Group of Companies. LEED is a registered trademark of the US Green Building Council.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG Architectural Coatings
One PPG Place
Pittsburgh, PA 15272
www.gliddenprofessional.com/THD

Technical Services
1-800-454-3336

A2.42 4/2014

Made in the
USA